



XP1239 TENT

COMPOSITION

100% polyester + FR PU coated

FABRIC PROPERTIES

Number of ends (warp)	.	17 DR/CM
Number of picks (weft)	.	12 DR/CM
Usable width	151.0	CM
Full width	Full width	150.0
Weight with a deviation of 4%	EN 12127 meth 5	275 G/M ²
Construction	Weft Rips 2/2	

PROPERTIES

Tensile Strength warp	ISO13934-1 2013	1800 N
Tensile Strength weft	ISO13934-1 2013	1200 N
Tear Resistance Elmendorf warp	ISO13937-1 2000	50 N
Tear Resistance Elmendorf weft	ISO13937-1 2000	40 N
Tear Strength (3 legs) warp	ISO4674 1A 2003	110 N
Tear Strength (3 legs) weft	ISO4674 1A 2003	100 N
Spray Test EN 24920	100 ISO 5	
Watercolumn EN 20811/ISO811	5000	mm
Shrinkage oven 1min-190°C - warp	shri oven 1min	-3,50 %
Shrinkage oven 1min-190°C - weft	shri oven 1min	-1,00 %
40°C Wash		
Tumble Dry	✓	
Dry Clean	x	
Iron	✓	

COLOURFASTS

		Light	Middle	Dark	Change
Colourfastness to light	ISO105B02 2014	6	6	6	

CERTIFICATES

DIN 4102-B1	DIN 4102-B1
-------------	-------------

REMARKS

Treated for transfer printing

Flame retardant EN ISO 15025 A1

The values on this sheet are solely indicative and are in no way binding for Xpres

01332 85 50 85 xpres.co.uk