

XTRA STRETCH®

XP3061 - 50cm wide

Xtra Stretch® is recommended for stretch and performance fabrics due to its soft silk finish and added flexibility. This textile transfer film is suitable for fine detailed logos as it has an adhesive backing and since Xtra Stretch can be peeled hot or cold it's capable of faster production.

A4 samples are available free of charge upon request, for larger samples 1m rolls are available to purchase.

STEP BY STEP

STEP 1

Cut your design in mirror image. Film blade required.

STEP 2

Weed away any excess material.

STEP 3

Place transfer face down onto the garment with the transparent backing on top and press for 15 seconds at 155°C.

STEP 4

Remove the transparent backing hot or cold.

DURABILITY	MICRONS	FINISH	TACK	PEEL	PU OR PVC
60°C	90	Matt	High	Hot	PU

PRODUCT INFORMATION

SIZE:	50cm wide x 1m, 5m, 25m rolls
CUTTING FORCE:	Film Blade (0.25) from 30gf *
TRANSFER LAYERING:	Yes (excluding metallics)

SUITABLE FOR

COTTON
POLYESTER
LYCRA & BLENDS

ACCREDITATIONS

OEKO-TEX®
 CONFIDENCE IN TEXTILES
 STANDARD 100
 HOHENSTEIN HTTI
 Tested for harmful substances
 www.oeko-tex.com/standard100

CLASS 1



TRANSFER SETTINGS

TIME	15 seconds (re-press for 5 seconds when multi layering)
TEMP	155°C
PRESSURE	Medium / Heavy
PEEL	Hot or Cold

CARE INFORMATION

WASH UP TO 60°C
DO NOT DRY CLEAN
CAN BE TUMBLE DRIED
CAN BE IRONED
STORAGE (Store vertically in a dry room between 15-30°C)

* All force testing has been undertaken using a NEW blade on a Roland GS24. The force will increase with the age of the blade, therefore always test prior to use.

PLEASE NOTE: The sellers and manufacturers maximum obligation shall be to replace any product that has been proven to be defective. Neither the seller nor the manufacturer of Xtra Stretch shall be liable for any injury direct or consequential, arising out of the use of, or inability to use this range. Xtra Stretch has been tested using Kustom Kit garments, when applying to other garment brands results may vary, testing prior to purchase is recommended.