

## REFLECTIVE

XP3010 - 50cm wide

Reflective is perfect for the production of high visible reflective logos for application onto many different textile compositions, including nylon jackets, bags and umbrellas, plus cotton & polyester garments.

A4 samples are available free of charge upon request, for larger samples 1m rolls are available to purchase.

### STEP BY STEP

#### STEP 1

Cut your design in mirror image. Film blade required.

#### STEP 2

Weed away any excess material.

#### STEP 3

Pre-press the garment for 4 seconds, then place the transfer face down onto the garment with the transparent backing on top and press for the recommended settings

#### STEP 4

Open the press, remove the garment from the heat press, wait 5-10 seconds and peel off the backing.

| DURABILITY | MICRONS | FINISH     | TACK | PEEL | PU OR PVC |
|------------|---------|------------|------|------|-----------|
| 40°C       | 175     | Reflective | High | Warm | N/A       |

### PRODUCT INFORMATION

|                           |                                |
|---------------------------|--------------------------------|
| <b>SIZE:</b>              | 50cm wide x 1m, 5m, 25m rolls  |
| <b>CUTTING FORCE:</b>     | Film Blade (0.25) from 110gf * |
| <b>TRANSFER LAYERING:</b> | No                             |

### SUITABLE FOR

**COTTON**  
**POLYESTER**  
**POLY/COTTON**  
**UNCOATED NYLON**

### ACCREDITATIONS



### TRANSFER SETTINGS

|                        |                                  |                    |
|------------------------|----------------------------------|--------------------|
|                        | <b>Pre-Press: 4 seconds</b>      |                    |
| <b>TIME &amp; TEMP</b> | Cotton / Polyester / Polycotton: | 160°C - 15 seconds |
|                        | Uncoated Nylon:                  | 150°C - 15 seconds |
| <b>PRESSURE</b>        | Medium                           |                    |
| <b>PEEL</b>            | Warm (wait 5-10 seconds)         |                    |

### CARE INFORMATION

**WASH UP TO 40°C**

**CAN BE DRY CLEANED**

**DO NOT TUMBLE DRY**

**DO NOT IRON**

**STORAGE** (Store vertically in a dry room between 15-30°C)

\* All force testing has been undertaken using a NEW blade on a Roland GS24. The force will increase with the age of the blade, therefore always test prior to use.

**PLEASE NOTE:** The sellers and manufacturers maximum obligation shall be to replace any product that has been proven to be defective. Neither the seller nor the manufacturer of Reflective shall be liable for any injury direct or consequential, arising out of the use of, or inability to use this range. Reflective has been tested using Kustom Kit garments, when applying to other garment brands results may vary, testing prior to purchase is recommended.